LUUM **Cross Dye**

Name

Cross Dye

Designer

Suzanne Tick

Style No.

4009

Use

Upholstery/Panel

Content

66% Recycled Polyester + 34% Polyester


Abrasion

Wyzenbeek 120,000 double rubs**

Environmental

Recycled Content





Earl Grey 4009-01








Light Birch 4009-03





Soft Shadow 4009-05



Ace Grey 4009-06



Cool Ash 4009-07







Crimson 4009-09



Carmine 4009-10



Tea Tree 4009-11





Plum 4009-13




Watercolor 4009-14



Azure 4009-15



Logwood 4009-16



Cross Dye by Luum

Cross Dye is a high performance action fabric ideal for task and guest seating. Its low price point is attractive for high volume and budget-oriented projects. It is made from 66% recycled polyester and is third-party certified to Facts Gold.

Name — Cross Dye

Style No. — 4009

Designer Suzanne Tick

Specification Use: Upholstery/Panel

Content: 66% Recycled Polyester (61% Postconsumer, 5% Preconsumer) + 34% Polyester

Weight: 14.8 ± 1 oz per linear yard

Width: 56.5"

Pattern Repeat: Horizontal 0.2" Vertical 0.13"

Directional: Yes

Finish Acrylic Backing

Performance Abrasion: ASTM D4157 Wyzenbeek 120,000 double rubs**

Breaking Strength: ASTM D5034 Warp 255.6 lbf, Fill 360.8 lbf Seam Slippage: ASTM D4034 Warp 82.5 lbf, Fill 68.6 lbf Colorfastness to Light: AATCC 16, Grade 5 at 40 Hours Colorfastness to Crocking: AATCC 8, Wet Class 5, Dry Class 5

Pilling: ASTM D3511 (Brush Pill), Class 5

Flame Retardancy Cal TB 117-2013

ASTM E84 Unadhered Class A or 1

Maintenance WS, Clean with either a water-based or solvent-based cleaning agent.

Environmental Facts 3rd-party certified to NSF/ANSI 336 Gold

Recycled Content

Origin Canada

Dye lots may vary slightly from samples shown. Samples shown off the bolt.

A # * * * o facts*

Canada 877.705.LUUM <u>luumtextiles.ca</u> **USA** 877.705.LUUM International 919.464.2922

cdn/us/int/05-16

 $\ensuremath{\mathbb{C}}$ Teknion 2016.

 * , $^{\text{\tiny{TM}}}$ Trademarks of Teknion Corporation and /or its subsidiaries or licensed to it.

Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance.

"Wyzenbeek results above 100,000 double rubs have not been shown to be a reliable indicator of increased fabric lifespan.

"Certification Marks owned by the Association for Contract Textiles, Inc.

U2-P3 — SC-305-4009