teknion philomina





philomina

teknion

STYLE Philomina

CONTENT 100% Polyester

WIDTH 160cm

WEIGHT 582 g/m

THICKNESS 0.79mm

COLORFASTNESS AATC 16: 2004 Option 3 - Xenon Arc Lamp Fading Test

TO LIGHT Grade 5 at 10 hours

WET & DRY AATC 116 - 2001

CROCKING Dry Crocking, Grade 5; Wet Cocking Grade 5

Dry Staining, Grade 4.5; Wet Staining Grade 5

ABRASION (12kpa) ASTM D4966-98 (2007) - Option 1 - Martindale tester

RESISTANCE At 20,000 Movemens

50,000 double rubs Wyzenbeck method

PHYSICAL Brush Pill - Class 5

PROPERTIES Breaking Strength - Warp: 431 lbs / Weft: 332 lbs

Seam Slippage - Warp: 68.2 lbs / Weft: 75 lbs

COLOR MATCHING Batch to batch variations in shade may occur within commercial tolerances.

Dye lots may vary slightly from samples shown.

Colors represented on this card are digital and intended to provide an overview of our textile program. Refer to individual samples to view actual material.

REMARKS: THESE RANGES OF PHILOMINA ARE ONLY AVAILABLE AT TEKNION MALAYSIA

WWW.TEKNION.COM

TO ORDER INDIVIDUAL SAMPLES, PLEASE VISIT WWW.TEKNION.COM OR CONTACT YOUR TEKNION REPRESENTATIVE. WHILE TEKNION USES EVERY EFFORT TO MAINTAIN STRICT STANDARDS AND CONSISTENCY OF FINISH, COLOR AND TEXUTRE THERE MAY BE SLIGHT VARIATIONS BETWEEN THE SAMPLES SHOWN AND THE ACTUAL PRODUCT.

ASIA CANADA USA

 TEL 603.3342.4345
 TEL 866.TEKNION
 TEL 877.TEKNION

 603.3342.3466
 866.835.6466
 877.835.6466

 INFO.TEKNION.
 INFO.CAN@TEKNION.
 INFO.US@TEKNION.COM

 MALAYSIA@TEKNION.
 COM

MALAYSIA@TEKNION. C

СОМ

EUROPE, SOUTH AND CENTRAL AMERICA, MIDDLE EAST, RUSSIA

OTHER OFFICES

FOR REGIONAL
INFORMATION GO TO
WWW.TEKNION.COM
TEL 416.661.3370
TEKINTL@TEKNION.COM

МҮ 10-17

© TEKNION 2017

 $\mathfrak{B}$ , TM TRADE MARKS OF TEKNION CORPORATION AND/OR ITS SUBSIDIARIES OR LICENSED TO IT. PATENTS MAY BE PENDING. SOME PRODUCTS MAY NOT BE AVAILABLE IN ALL MARKETS. CONTACT YOUR LOCAL TEKNION REPRESETNATIVE FOR AVAILABLILITY.

PRINTED IN MALAYSIA