muskoka

teknion



muskoka

teknion

STYLE Muskoka

CONTENT 100% Polyester

WIDTH 165cm

WEIGHT 460 g/m

ABRASION (12kpa) ASTM D4966-98 (2007) Option 1 - Martindale tester

RESISTANCE 21,000 cycles

PILLING ASTM - D3512-05 (2007) - Random Tumble - 30 mins

RESISTANCE Grade 4-5

COLORFASTNESS AATU 8 - 2007
TO CROCKING Dry Class 4-5
Wet Class 4-5

COLORFASTNESS Modified AATC 16: 2004 - Option 3 - Xenon Arc Lamp

TO LIGHT Exposure 40 hours

Grade 4-5

FLAMMABILITY CALIFORNIA TECHNICAL BULLETIN 117

Section E, Part 1, Pass

COLOR MATCHING Batch to batch variations in shade may occur within commercial tolerances.

Dye lots may vary slightly from samples shown.

Colors represented on this card are digital and intended to provide an overview of our textile program. Refer to individual samples to view actual material.

REMARKS: THESE RANGES OF MUSKOKA ARE ONLY AVAILABLE AT TEKNION MALAYSIA

WWW.TEKNION.COM

TO ORDER INDIVIDUAL SAMPLES, PLEASE VISIT WWW.TEKNION.COM OR CONTACT YOUR TEKNION REPRESENTATIVE. WHILE TEKNION USES EVERY EFFORT TO MAINTAIN STRICT STANDARDS AND CONSISTENCY OF FINISH, COLOR AND TEXUTRE THERE MAY BE SLIGHT VARIATIONS BETWEEN THE SAMPLES SHOWN AND THE ACTUAL PRODUCT.

ASIA CANADA US.

 TEL 603.3342.4345
 TEL 866.TEKNION
 TEL 877.TEKNION

 603.3342.3466
 866.835.6466
 877.835.6466

 INFO.TEKNION.
 INFO.CAN@TEKNION.
 INFO.US@TEKNION.COM

 MALAYSIA@TEKNION.
 COM

FOR REGIONAL

FOR REGIONAL
INFORMATION GO TO
WWW.TEKNION.COM
TEL 416.661.3370
TEKINTL@TEKNION.COM

OTHER OFFICES

EUROPE, SOUTH AND

MIDDLE EAST, RUSSIA

CENTRAL AMERICA,

МҮ 10-17

СОМ

© TEKNION 2017

(B), TM TRADE MARKS OF TEKNION CORPORATION AND/OR ITS SUBSIDIARIES OR LICENSED TO IT. PATENTS MAY BE PENDING. SOME PRODUCTS MAY NOT BE AVAILABLE IN ALL MARKETS. CONTACT YOUR LOCAL TEKNION REPRESETNATIVE FOR AVAILABLILITY.

PRINTED IN MALAYSIA